

STX 17-4 PH MIM

STX 17-4 PH MIM is a martensitic precipitation-hardening stainless steel based on the AISI 17-4 PH standard. It is characterized by a good combination of mechanical properties and corrosion resistance.

It is common in MIM, since the mechanical properties makes it possible to design parts, which retain a good strength. The secondary hardening can to some degree be done in the sintering process by adjusting parameters

Corrosionwise the material is on par with 304L, and can be substituted in many applications where the mechanical properties are required. Also the 304 powders are not available in bulk for MIM, so the 17-4PH is commonly used instead.

Chemical specification

The chemical composition of STX 17-4 PH MIM after sintering is as follows. (Measured in % of weight).

C	Cr	Ni	Cu	Mn	Si
< 0.07 %	15-17.5 %	3-5 %	3-5 %	< 1 %	< 1 %

Figure 1: Chemical specification for STX 17-4PH MIM

Typical properties

Properties can vary and can of course be adjusted to your application needs. It is however important to remember, that the properties are intercorrelated - demands on certain properties will offset values for other properties. If you e.g. have a need for higher hardness then it will influence elongation to a lower value. You have to be willing to forego other properties, if you have high demands in one area.

The challenge is to know what kind of properties are needed. Especially if it is the first times working with MIM. Many drawings are not designed with MIM in mind, but rather regular machining.

The best solution to this issue is to use our many years of design and production experience. Please consult our experts early in the process for further discussions and information regarding material selection and not least design possibilities. For some guidance however, here are the typical properties of finished sintered parts:

	Sintered	Heat treated
Density [% of theoretical]	≥ 98	≥ 98
Yield strength Rpo.2 [MPa]	650 - 750	≥ 950
UTS Rm [MPa]	800 - 950	≥ 1100
Elongation [%]	≥ 6	≥ 4
Hardness [Hv10] (HRC)	≥ 320 (32 HRC)	≥ 370 (38 HRC)

Figure 2: Typical properties for STX 17-4 PH MIM

Feedstock

The feedstock consist of a binder system mixed with metal powders in a certain concentration. The higher you are able to load the binder system with powder, the less the part shrink in the end. There is however an upper threshold of around 63% powder in such a system, since above that there is so much metal that a metal "bridge" is formed when mixing it and this will cause inhomogeneity. Hence in order to stay away from this limit, most feedstocks consist of around 60% powder and 40% binder.

Within the chosen material, the powders can also be of different types and give different properties. We divide them in 3 groups: Prealloy, Master alloys and Engineering alloys. Each of them has different strengths and weaknesses - all is in the details on how the powders work during sintering. Please see figure 3 below. The final powder is selected to match the components desired.

Figure 3: Strength and weaknesses of the various powder types and comparison hereof

Property	Pre-alloy	Master-alloy	Engineering alloy
Density	Very good	Good	Less good
Polishability	Very good	Good	Less good
Moldability	Very good	Good	Less good
Surface finish as sintered	Very good	Good	Less good
Geometrical stability	Very good	Good	Less good
Material price	Very good	Good	Less good

 = Very good  = Good  = Less good

Rethinking Components of Tomorrow

Rikke Pilgaard

Key Account Manager

Telephone: +45 9657 4394
 Email: rpr-sintex@grundfos.com
 www.sintex.com



Sintex® Metal Injection Moulding

The MIM process and MIM components

The MIM process is in reality just 3 simple steps after the feedstock has been mixed and supplied - namely molding, debinding and sintering. The process and the intermediate parts are illustrated below.




Figure 4: Illustration of the MIM process

Metal Injection Moulding is a fantastic unique technology, but it might not be the best choice for your component. It is a complex technology and some parts are less suited for MIM even though it is such a simple process.

In our opinion the best way to consider is to involve MIM experts early in the process. Some considerations may be able to be changed early in the process, plus the unique feature of MIM - to be able to combine several components in one - may also be considered.

One to one conversion of previous metal parts to MIM parts is generally not a good idea. For the best result, all possibilities should be considered. Savings on assembly processes or finishing treatments might be the parameters that make the MIM process attractive financially as well.



Another possibility, worth mentioning as an example, is to have logo, batch or serial number recessed in the parts.

Basic considerations & Design guidelines

There are some basic rules that can both help evaluate the component for the MIM process but also help in the initial phase of designing the tool and molding. These are:

- Component weight 0.1 – 250 g
- Tolerance level (+/- 0.5% of the nominal value)
- Think geometry - how is it possible to place part during sintering?

Smaller or larger components have been made, tolerances have been smaller but then you are outside the comfort zone of the process.

Besides these basic rules there are also general design guidelines. These are illustrated and shortly described in figure 5.




Figure 5: Design guidelines

Results

The data for STX 17-4 PH MIM shown in this data sheet has been obtained in cooperation with our feedstock suppliers in accordance with ISO standard 22068. It is not possible to directly attribute all the results to specific components, as parameters such as powder flow, component size and geometry can have an effect on the properties of the individual components.

Version 2017-02-27

Rethinking Components of Tomorrow

Rikke Pilgaard

Key Account Manager

Telephone: +45 9657 4394
Email: rpr-sintex@grundfos.com
www.sintex.com

